

8S***Bathroom and Kitchen Silicone Sealant***

Technical Data Sheet

January 2004

Product Information***Description***

Z Bond 8-S is a one component, non-flowing, ACID cure, MID modulus silicone sealant. It cures by absorption of atmospheric moisture to form a flexible and durable elastomeric sealant.

Special Features

Z Bond 8-S contains an effective fungicide to reduce the growth of mould and mildew. It is a fast curing system that offers very good adhesion to glazed ceramic and enamel surfaces.

The thixotropic nature of this product ensures that it will not slump in typical construction joints.

Typical Uses

Seal for wet areas in kitchens and bathrooms.

One Part System

Being a one-part sealant Z Bond 8-S offers the confidence of consistent even cure. It also improves operator productivity, as time is not lost mixing the product, is easy to use in difficult locations, and can be applied out of a standard cartridge gun

Packaging

The standard packaging for Z Bond 8-S is 300ml polyethylene cartridges. We can pack it into many different containers, please contact your local agent for details of minimum order size, lead-time and dispensing methods.

Long Life Reliability

Z BOND 8-S has excellent natural ageing stability. It will maintain its elastomeric joint sealant properties permanently, even under harsh conditions and temperature extremes.

Characteristics***System Properties***

Property	Mean Result Achieved	Test Method
Skin Time	6 Minutes	BS 5889
Tack Free Time	30 Minutes	ASTM C679
Tooling Time	10 Minutes	ASTM C679
Sag or Slump	Nil	MIL-A-46106A



RHODIA AUSTRALIA PTY LTD A.B.N. 24 050 029 000
 352 Ferntree Gully Road, Notting Hill, Vic 3168, Australia.
 Postal Address PO Box 1544, Clayton South, Vic 3169, Australia
 Telephone: (613) 9541 1000 Toll Free 1800 802 493

Cured Properties

Property	Mean Result Achieved	Test Method
Shore A Hardness	20	ASTM C 661
Modulus at 100% Elongation	0.40 MPa	ASTM D 412
Tensile Strength	1.80 MPa	ASTM D 412
Elongation at Rupture	520%	ASTM D 412
Peel Strength after UV through Glass	50N/25mm	FED TT-S-00-1543A
Dynamic Movement Capacity	± 20%	ASTM C 920
Accelerated Ageing and Weathering	Excellent	ASTM C 792

Temperature

	Minimum	Maximum
Application Temperature	-10 ⁰ C	+40 ⁰ C
Service Temperature	-50 ⁰ C	+150 ⁰ C

Application of the sealant at -10⁰C is permissible provided the surface to receive the silicone is dry and free of frost. The maximum service temperature listed is for transient temperatures; the silicone sealant will deteriorate if subjected to these temperatures on a continuous basis.

Colours

Translucent; White

We can manufacture silicone sealants in almost any solid colour. To manufacture a special colour we need a sample of the required colour, and a single purchase order covering the full batch quantity. There could be a small additional charge to cover colour matching costs, or special pigments.

Sealant Application

Joint Design

The sealant must be capable of withstanding the expected joint movement. To calculate the joint width, establish the expected movement (expansion, contraction and shear movement) that the joint is required to withstand. The dynamic movement capability of Z BOND 8-S is ± 20%. The Data Sheet on Joint Design contains the formula for calculating the required joint width from the expected joint movement and the dynamic movement capability of the sealant.

The joint design must avoid three-sided adhesion.

The sealant depth for a weatherseal is normally half the joint width. The minimum acceptable joint depth is 6mm; therefore, if the required joint width is 6mm the depth is also 6mm.

Back up Material

Use a closed cell polyethylene-backing rod, 25% larger than the joint width, to control the depth of the joint.

Compatibility with Adjacent Substrates

Silicones are not always compatible with plasticised sealants, such as butyls. Also some backing rods and glazing tapes contain bitumen or other agents that are incompatible with the silicone. The incompatibility may cause discolouration, poor sealant cure or long term degradation of the sealant. Always carry out compatibility tests where contact with potentially incompatible materials occurs.

Application

Always ensure that the surfaces to be sealed are dry and free from oil, dirt and grease. Use the two-wipe process for impervious substrates. Ensure the cloths are clean and changed frequently, and use a suitable solvent such as Z Bond R-40, I.P.A. or White Spirits. Typical substrates are glass, aluminium and Zinalume. For porous surfaces, abrade the surface to remove loose particles, and surface contaminants. When extruding the sealant cut the nozzle to the desired width, cut the tip

off the cartridge, and apply the sealant firmly to ensure good contact between the sealant and the substrate. Before the sealant has skinned, tool it off to ensure a good finish, and to improve the wetting out of the sealant to the substrate.

To achieve satisfactory adhesion a primer may be required for some substrates. Consult the manufacturer or your distributor for more information.

Curing

Z BOND 8-S cures by absorbing atmospheric moisture, it will skin over in 6 minutes and cure to a depth of 9mm in 7 days.

Design Support

Because of the importance of Surface Preparation, Sealant Application and Joint Design Rhodia Australia Pty. Ltd. provide specific Data Sheets on these topics. These data sheets are available free of charge, and we strongly recommend that you consult these sheets before commencing application of the sealant. We will also review shop or working details, test substrates, and associated materials for compatibility and adhesion, and make sealant recommendations when requested.

Storage and Shelf Life

Always store the sealant in a cool dry place. Ideal storage temperature is not more than 25°C. Prolonged storage at high temperatures may affect shelf life and ultimate performance. The shelf life of Z BOND 8-S is 9 months from the date of manufacture when stored below 25°C and below 50% relative humidity.

Limitations

Z BOND 8-S is NOT suitable for use in the following applications: -

- As the sealant requires atmospheric humidity to cure, it will not cure in totally confined spaces where it does not have access to atmospheric humidity.
- Product is not recommended for use in sealing application in frequent contact with flowing water.
- Aquariums
- Adhering Mirrors
- Laminated Glass
- Reflective Glass
- Structural Glazing
- Under Water Applications (including swimming pools)
- N. B. This product is suitable for some applications where the sealant is in contact with water for extended periods. Please contact Rhodia Australia Pty. Ltd. to confirm your design details before commencing such an application.
- Below Grade Applications
- Concrete, cement or masonry
- Stone (We recommend the completion of a stain testing program before using any sealant on stone)
- Soft metals, such as galvanising, Zinalume[®], brass and bronze, and
- Horizontal walkways.
- This silicone is not paintable. If there is a requirement to paint the sealant our recommendation is to use our Z Bond Multi Purpose silicone sealant or Z Bond Gap Filler acrylic sealant products. Follow both the sealant and paint manufacturers painting instructions carefully, when painting sealants.

Health and Safety

Z BOND 8-S is not classified as Dangerous Good or Hazardous Substance according to the ADG Code and Worksafe Australia respectively. The product however, should be used in accordance with good occupational, health and safety practices. The product however, should be used in accordance with good occupational, health and safety practices. May cause irritation if swallowed, moderately irritating to eyes, vapour may cause irritation during the cure stage (if vapour in high concentrations). It releases Acetic acid until fully cured.

Do not swallow and avoid prolonged or repeated contact with the skin. If contact with the eyes occurs, wash eyes with copious quantities of water and consult a doctor if irritation persists.

The Material Safety Data Sheet defining the known hazards and describing the appropriate safety precautions with respect to the product is available through Rhodia Australia Pty. Ltd.

Important Notice for Users

RHODIA'S SOLE WARRANTY IS THAT ITS PRODUCTS WILL MEET RHODIA'S THEN CURRENT SALES SPECIFICATIONS, WHICH ARE AVAILABLE THROUGH ITS COMMERCIAL AGENCY.

We based the Information and data contained in this publication on our current knowledge of the product. The properties of individual batches of sealant may vary from the results published as mean results achieved, however our Quality Control System will ensure they are always within an acceptable tolerance of the published figures. As the application, use and processing of the product are beyond our control Rhodia disclaims any warranty for fitness for use or for a particular purpose.

Rhodia Australia Pty. Ltd. provides a comprehensive testing service, in our Quality Control Laboratory. Where particular performance criteria are required we strongly recommend that a testing program be carried out, prior to the commencement of the project.

Suggestions for use should not be taken as an inducement to infringe any particular patent.

* Z Bond is a registered trademark of RHODIA